

Sr. No. : 0128

Original

sasmira

The Synthetic & Art Silk Mills' Research Association

(APPROVED BODY BY MINISTRY OF TEXTILES, GOVT. OF INDIA)
SASMIRA MARG, WORLI, MUMBAI - 400 030.

Tel. : 2493 5351/52, 2493 2047, 2493 8753/54 (EPBX)
E-mail : ed@sasmira.org • testing@sasmira.org

Fax : 91-22-2493 0225
Web : www.sasmira.org

TEST REPORT

Test Report No : SASMIRA/1887/20-21	Date : 03 Apr 2021
Name & Address of Customer :	Clique Medical Solutions Pvt. Ltd. 2B, 1806, Dreams Complex, Behind Dreams Mall, Bhandup (West) Mumbai - 400 078
Sample Forwarding letter No :	Mail dated 27/03/2021
Date of Receipt : 30 Mar 2021	Date of Testing : 30 Mar 2021 - 03 Apr 2021
Particulars of Sample given by the customer :	One fabric sample

Discipline : Mechanical

Product Group : Textile

Sample : Sample 2: Thermaissance Fabric (Blue Colour)

Sl No	Test Name	Method	Results
1	Ultraviolet Protection factor (UPF) UPF Rating UV-A Blocking % UV-B Blocking %	AATCC 183	141 99.1 % 99.4 %

Note :


* This test does not fall under the scope of accreditation.

* Small portion of the submitted sample is enclosed herewith for reference.

-- End of the test reports --

AUTHORISED SIGNATORY

Mrs. L. V. Mhatre



NOTE : L / 04 / 05

- The result relate only to the samples submitted
- The test report shall not be reproduced except in full, without written approval of the laboratory and shall not be used for publicity or litigation
- The sample/s tested and reported is / are not drawn by the laboratory.

- Sample conditioning and testing : a) For IS, IS/ISO Test Method: Temp. of 27±2°C and Humidity of 65±2%, b) For ASTM & AATCC Test Method: Temp. of 21±2°C and Humidity of 65±5% and c) For ISO/DIN/JISL Test Method: Temp. of 20±2°C and Humidity of 65±2%
- The rating for Pilling test varies from 1 to 5, where 1 is "severe pilling" and /or "Dense surface fuzzing" and 5 is "No change".
- The rating for Change in shade/ Staining varies from 1 to 5 where 1 is poor and 5 is excellent.